

PRODUCT DESCRIPTION:

DUREX DECORATIVE STUCCO is a cement based vinyl modified stucco, formulated for application using a variety of texturing methods. Various attainable textures include flat, spanish style, adobe, spray and other unique custom designed textures and patterns.

USES:

DUREX DECORATIVE STUCCO is an economical quality texturing product which can be used for both exterior and interior applications on walls and ceilings as a final texture finish.

DUREX DECORATIVE STUCCO can also be used as a base coat to smooth out irregularities in substrates, such as misaligned concrete pours and poor joints in masonry construction.

ADVANTAGES:

- economical
- various texture finishes; texture limited only by user's imagination
- can be applied by trowel, spray and other methods

such as sponge, broom etc.

- regulated set time
- only add potable water for mixing
- excellent adhesion over a wide number of substrates
- hard wearing surface, not easily damaged

LIMITATIONS:

DUREX DECORATIVE STUCCO is not recommended for use:

- below grade
- when ambient, surface and material temperatures are below 5°C (41°F) during application and curing period
- on unprimed wood, drywall and cementitious board surfaces

MIXING PROCEDURES:

DO NOT SUBSTITUTE NOR COMPENSATE **DUREX DECORATIVE STUCCO** WITH OTHER ADDITIVES. Discard all materials which have begun to harden.

Mix **DUREX DECORATIVE STUCCO** with potable water using a low speed paddle mixer. Mix until free

TECHNICAL DATA

Physical Properties:

Product type:	Cement based stucco
Appearance:	White powder with fine aggregates
Toxicity:	CAS Registry No. 65997-15-1 (contains Portland Cement)
Bulk density:	1290 kg/m ³ (80 lb/ft ³)
Bulk pot life:	3 hrs. to 6 hrs. (depending on temperature and humidity)
Mixing ratio:	1 bag DUREX DECORATIVE STUCCO 9 litres water (2 gallons)
Coverage:	Coverage will vary according to texture selection and texturing method used.
Average coverages:	Fine texture – 13.9 m ² (150 ft ²)/bag Med texture – 9.3 m ² (100 ft ²)/bag Coarse texture – 4.6-7.0 m ² (50-75 ft ²)/bag
Substrate requirement:	Clean concrete, cement stucco base or alkyd primed drywall.

092222

DECORATIVE FINISHES
EXTERIOR/INTERIOR STUCCO FINISH

of lumps. Let stand for 10 to 15 minutes. Retemper and use. Mix 1 bag of **DUREX DECORATIVE STUCCO** to 9 litres of water. Mix initially to a paste-like consistency. If desired, at time of retempering the viscosity of the mix can be adjusted to suit the method of application selected. Do not over dilute mixture as surface fine cracking will result.

Consult **Durabond Products Limited** for recommendations for mixture adjustment.

Avoid overmixing as it will induce air into the mix which can result in surface fine cracking. Discard all mixed materials which have begun to stiffen a second time.

APPLICATION:

Substrate surfaces must be clean and sound, free of weak and powdery surfaces, dust, dirt, oil, grease and other deleterious materials detrimental to a positive bond. Do not apply materials to wet, frozen, nor frosted substrates.

Check with **Durabond Products Limited** for recommendations for mixture adjustment.

Glossy surfaces must be dulled by sanding and left clean as specified above.

Wood: Prime all interior and exterior wood surfaces with minimum two (2) coats of a stain blocking primer. Allow to dry between coats.

Drywall, Cementitious Boards and Plaster: Prime all surfaces with one coat of a good quality alkyd flat white primer. Allow to dry overnight before applying the stucco finish.

Masonry: Remove all loose material and dampen (fog spray) surface before applying stucco. Pre-fill all large cracks, holes and joints with stucco mix and allow to dry before applying the stucco finish.

Trowel apply a levelling base coat of **DUREX DECORATIVE STUCCO** over concrete surfaces to a smooth, straight and true surface. Apply to a maximum thickness of 3.2 mm (1/8"). Allow the base coat to dry a minimum of 24 hours before proceeding with the final texture finish.

Over masonry walls apply two levelling base coats of **DUREX DECORATIVE STUCCO**, each coat applied to maximum thickness of 3.2 mm (1/8"). Allow each coat to dry a minimum of 24 hours before proceeding with the final texture finish. Do not apply the base coat in layers thicker than 3.2 mm (1/8") as cracking may result.

Note: It is advisable to experiment with tools and viscosity to produce the required finish

before proceeding with the entire project.

Allow a minimum of 24 hours for curing between coats.

Protect freshly applied stucco system from inclement weather until materials have fully set and cured. Prevent rapid evaporation.

CLEAN-UP:

Clean all tools promptly after each use with clean water. Do not allow mixes to dry on tools, as removal may be difficult.

STORAGE:

Store **DUREX DECORATIVE STUCCO** in a dry, vented, waterproof location, stacked off the ground with ambient temperatures above 5°C (41°F). Keep materials dry, protected from rapid temperature changes, dampness and moisture and away from direct sunlight.

KEEP FROM FREEZING.

PACKAGING:

DUREX DECORATIVE STUCCO is available in 20 kg (44 lb) bags.

COVERAGE:

One bag of **DUREX DECORATIVE STUCCO** will yield approximately 5 gallons of matrix. Average coverage will be approximately 14 m² at 3.2 mm (150 ft² at 1/8") thickness. A test sample should be applied to establish practical coverage of the selected texturing method.

WARRANTY:

Durabond Products Limited fully warrants their products when used and applied in strict accordance with the printed instructions on product mixing and product application. In any case **Durabond's** responsibility shall not exceed either the refund of the purchase price, or the replacement of the purchased product.

TECHNICAL SERVICES:

Technical assistance for unique applications and design is available upon request from **Durabond Products Limited**.

DURabond

Manufacturers and Distributors of High Quality Construction Products

55 Underwriters Road, Toronto, Ontario M1R 3B4

Tel: (416) 759-4474 Toll Free: 1-877-DURABOND (387-2266) Fax: (416) 759-4470

Email: info@durabond.com Website: www.durabond.com