

**PRODUCT DESCRIPTION:**

**DUREX MONOBASE NC** is a single component polymer based non-combustible cementitious mortar which has been developed to utilize advanced polymer technology to combine the strength and toughness of polymer modified cement with the flexibility of synthetics.

**USES:**

**DUREX MONOBASE NC** mix is used as the base coat in “**Durex Insulite, Durex Insulite EW-17, Durex Insulite EW-17 Select, Durex Quantum, Durex Insulite EXT and Durex Insulite EXT-Select Wall Systems.**”

**ADVANTAGES:**

**DUREX MONOBASE NC** has been formulated to provide a highly flexible cement based coating which is crack resistant. It can be bent over a 6.4 mm (1/4") mandrel without cracking. **DUREX MONOBASE NC** provides the following features:

- superior adhesion to various inorganic substrates

- combines the strength of cement and the flexibility of synthetics
- designed to allow minor movements up to 1.6mm (1/16") in the substrate without causing cracking in the base coat
- allows for large surface areas to be coated without the need of unwanted control joints
- ready to use; just add water
- excellent job site quality control

**LIMITATIONS:**

- Mix **DUREX MONOBASE NC** only with clean, potable water
- Ambient, surface and material temperatures must be above 5°C (41°F) during application and curing period
- Do not apply the mix in layers thicker than 3.2 mm (1/8") in any one pass

**MIXING PROCEDURE:**

DO NOT SUBSTITUTE NOR COMPENSATE THE **DUREX MONOBASE NC** MIX WITH OTHER ADDITIVES.

**TECHNICAL DATA**

**Physical Properties:**

<b>Product type:</b>	Polymer based plaster mixture.
<b>Appearance:</b>	Grey cementitious powder.
<b>Toxicity:</b>	CAS-Registry No. 65997-15-1 (contains Portland Cement).

**Performance Characteristics:**

Test	Method	Results
<b>Tensile strength:</b>	ASTM C190-85 ASTM C190-85	0.35 MPa (50 psi) without mesh 16.55 MPa (2400 psi) with mesh
<b>Elongation:</b>		9.4%
<b>Flexural strength:</b>	ASTM C293-70	8.28 MPa (1200 psi)
<b>Air Leakage:</b>	ASTM E283-91	0.0174 L/s.m2 @ 1.5 mm thick 0.0022 L/s.m2 @ 3.0 mm thick Class 3 air barrier
<b>Water Vapour Permeance:</b>	ASTM E96-95	385.56 ng/Pa.s.m2 @ 25°C
<b>Fire Rating:</b>	CAN/ULC S114	Rated non-combustible

092222

**DUREX MONOBASE NC**  
POLYMER BASED CEMENT PLASTER

Thoroughly mix **DUREX MONOBASE NC** before each use. Discard all materials which have formed solid lumps at the bottom of the container and materials which do not appear to be of a homogeneous viscosity. Discard all frozen materials. Discard all material which has begun to harden.

Mix **DUREX MONOBASE NC** with clean, potable water in accordance with the following formula:

<b>WATER</b>	5 liters
<b>monobase NC</b>	1 bag

Pour **DUREX MONOBASE NC** clean potable water into an empty clean mixing container. While under slow mixing action add the **DUREX MONOBASE NC** in the required mixing proportions. Mix well until the mixture is free of lumps. Do not over-mix nor use excessive mixing speed.

Let mixed material stand for approximately 15 minutes. Mix only enough materials which can be used within 1 hour. Working time may vary slightly depending on temperature and relative humidity. Retemper and use. Discard all materials which have begun to stiffen for a second time.

#### **APPLICATION:**

Refer to the selected Durex Wall System for the application of **DUREX MONOBASE NC**.

#### **CLEAN-UP:**

Clean all tools promptly after each use with clean water. Do not allow mixes to dry on tools.

#### **STORAGE:**

Store **DUREX MONOBASE NC** in a dry, vented, waterproof location, stacked off the ground and with ambient temperatures above 5°C (41°F). Keep materials dry, protected from rapid temperature changes, dampness and moisture and away from direct sunlight.

KEEP FROM FREEZING.

#### **PACKAGING:**

**DUREX MONOBASE NC** is readily available in 22.7 kg (50 lb) bags.

#### **COVERAGE:**

Each pail/bag will provide approximately 9 m<sup>2</sup> (100 ft<sup>2</sup>) at 3.2 mm (1/8") thickness.

#### **WARRANTY:**

**Durabond Products Limited** fully warrants their products when used and applied in strict accordance with the printed instructions on product mixing and product application. In any case **Durabond's** responsibility shall not exceed either the refund of the purchase price, or the replacement of the purchased product.

#### **TECHNICAL SERVICES:**

Technical assistance for unique applications and design is available upon request from **Durabond Products Limited**.

# DURABOND

Manufacturers and Distributors of High Quality Construction Products

55 Underwriters Road, Toronto, Ontario M1R 3B4

Tel: (416) 759-4474 Toll Free: 1-877-DURABOND (387-2266) Fax: (416) 759-4470

Email: [info@durabond.com](mailto:info@durabond.com) Website: [www.durabond.com](http://www.durabond.com)